## Nurcacit DPTU Thiourea Accelerator

## **Technical Data Sheet**

CHEMICAL NAME: N,N'-Diphenylthiourea

CAS NO.: 102-08-9

STRUCTURE: N = N = C = N = C

This product can be used as the fast vulcanization accelerator of the natural latex and chloroprene rubber latex. It also can be used as the polyvinyl chloride's heat stabilizer of emulsion polymerization, especially suitable for the soft products, can't be used simultaneously with such stabilizers as the lead, cadmium, etc., otherwise will cause the products to change color. Used in electric wire, cable, rubber overshoes, rain shoes, curing bladder, rubber bag, etc. products.

| PRODUCT SPECIFICATIONS        |          |                                       |              |
|-------------------------------|----------|---------------------------------------|--------------|
|                               |          | Pdr                                   | Оср          |
| Appearance:                   |          | White powder                          | White powder |
| Melting Point Initial         | (℃) min. | 148.0                                 | 148.0        |
| Heating Loss                  | (%) max. | 0.30                                  | 0.50         |
| Ash                           | (%) max. | 0.30                                  | 0.30         |
| Residue on 150 $\mu$ m sieve: | (%) max. | 0.10                                  | 0.10         |
| Residue on 63 $\mu$ m sieve:  | (%) max. | 1.0                                   | 1.0          |
| Additive                      | (%)      |                                       | 0.1-0.2      |
| PACKAGING:                    |          |                                       |              |
| Bag:                          |          | 25kg paper bag with PE-Inlay          |              |
|                               |          | Or other kind of package clients need |              |
| STORAGE                       |          |                                       |              |

stored in the dry and cooling place with good ventilation, avoiding exposure to direct sunlight

Shelf Life: 12 months

Add: Rm N, 20FI, Building B, New World Center 88# Zhujiang Rd. Nanjing 210008 China

地址: 中国. 江苏. 南京。珠江路 88 号 新世界中心 B 幢 20 楼 N 座 邮编: 210008 Contact: Tel: +86 25 8446 2798 Fax:+86 25 8446 3798 Email: info@nurchem.com

www.nurchem.com