

**Nurcacit HMDC**  
Curing Agent**Technical Data Sheet**

CHEMICAL NAME: Hexamethylene diamine carbamate

CAS NO.:143-06-6

It is mainly used as curing agent for AEM rubber, fluoroelastomers, PU, also used as modifying agent for synthetic rubbers and curing active agent for natural rubber, butyl rubber, isoprene rubber, styrene butadiene rubber, etc.

**PRODUCT SPECIFICATIONS**

Appearance:		White Powder
Content	(%) min.	99.5
Melting Point	(°C)	155-160
Moisture	(%) max.	0.2
Average particle size	( $\mu$ m) max.	15

**PACKAGING:**

Drum: 250kg/plastic bag. 20bag/carton or 25kg fiber drum

Shelf Life: 24 monthes