

Nurcastab 900/911/921
Plastic Antioxidant

Technical Data Sheet

| | | | |
|---|--|---------------|----------|
| CHEMICAL NAME: | Mixture of Nurcastab 1076 and Nurcastab 168 | | |
| CAS NO.: | Nurcastab 1076: 2082-79-3 Nurcastab 168: 31570-04-4 | | |
| Structure: | Not available | | |
| SPECIFICATIONS | | | |
| ◇ Appearance: | White powder | | |
| ◇ Transmittance (%) : | 425 nm: | 96 min | |
| | 500 nm: | 98 min | |
| ◇ Volatile (%) : | 0.5 max | | |
| ◇ Solubility (2g/20ml, Toluene): | Limpidity | | |
| ◇ Ratio: | Nurcastab-900 | 1:4(±5%) | |
| | Nurcastab 1076: | Nurcastab-911 | 1:1(±5%) |
| | Nurcastab 168 | Nurcastab-921 | 1:2(±5%) |
| Applications: | | | |
| Nurcastab 900, Nurcastab 911, Nurcastab 921 are now products with excellent effect in antioxidizing and have economical price. They have long protecting effect on polymer and are widely used in polyolefins (PE and PP), polyamide, polycarbonate, PBT and ABS etc. Recommended Dosage: 0.1-0.5% | | | |
| Package: | | | |
| 20kg paper bag; Pallet weight:600Kg | | | |